

DARACEM[®] 100

High-range water-reducing admixture ASTM C494 Type F and G and ASTM C1017 Type I

Product Description

DARACEM[®]100 is an aqueous solution of chemical dispersants combined with other chemicals which increase its beneficial effects on the quality and plasticity of a concrete mix.

Daracem 100 is the first high-range water reducer specially formulated for extended slump life. Conventional superplasticizers normally provide only 25 to 45 minutes of slump increase before the concrete begins to lose workability. Daracem 100, however, extends the time span of the slump increase up to twice as long or longer. One gallon of Daracem 100 weighs approximately 10 lbs (1.2 kg/L).

Uses

Daracem 100 provides improved slump retention in flowable concrete. It is ideal for low water/cement ratio concrete designed for high early compressive and flexural strengths with exceptional workability and flow characteristics. Because of its unique ability to draw maximum effect from the cement content of a mix, it frequently gives performance with a Type I cement comparable to that of a Type III cement.

Daracem 100 helps to solve difficult placeability problems such as dense rebar networks or constricted forms and job conditions requiring that the concrete be transported or pumped for long distances. A Daracem 100 mix flows easily into forms and around reinforcing steel. Even at high slump, the concrete consolidates well without segregation.

Product Advantages

- May be used as an ASTM C494 Type F and G high-range water-reducing admixture
- Can produce high slump flowable concrete with no loss in strength
- Can produce low water/cement ratio concrete and therefore, high strengths
- Concrete produced with Type I cement may be substituted for normal concrete produced with Type III cement to achieve early strengths
- At high slump, exhibits no significant segregation in comparison to concrete without a superplasticizer at the same slump

Addition Rates

Daracem 100 can be added at variable addition rates to suit job requirements. The normal dosage range is 5 to 20 oz/100 lbs (325 to 1300 mL/100 kg) of cement. In the lower range, Daracem 100 meets the requirements for an ASTM C494 Type F water-reducing, high-range admixture and at the upper range for a Type G water-reducing, high-range and retarding admixture. Note that when used as a Type G admixture, concrete set times will increase. Varying addition rates may give added slump variances to match placement needs. Should job conditions require more than recommended addition rates, please consult your GCP representative.

Compatibility with Other Admixtures and Batch Sequencing

Daracem 100 is compatible with most GCP admixtures as long as they are added separately to the concrete mix, usually through the water holding tank discharge line. However, Daracem 100 is not recommended for use in concrete containing ADVA[®] superplasticizers or polycarboxylate-based mid-range water reducers. In general, it is recommended that Daracem 100 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

Pretesting of the concrete mix should be performed before use, as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as DARAVAIR[®] or DAREX[®] II AEA) is recommended to provide suitable air void parameters for freeze-thaw resistance. Darex AEA is not recommended.

Packaging & Handling

Daracem 100 is available in bulk, delivered by metered tank trucks, totes and drums.

Daracem 100 will begin to freeze at 32 °F (0 °C) but will reconstitute to full strength after thawing and agitation. In storage and for trouble-free dispensing, Daracem 100 should be maintained at temperatures above 40 °F (4 °C).

Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available.

gcpat.it | Servizio clienti in Italia:: +39 02 93537291

Confidiamo che le informazioni date con la presente siano utili. Sono basate su dati e conoscenze che riteniamo vere ed accurate e sono messe a disposizione dell'utente perché li consideri, facendo le opportune verifiche. Tali informazioni non rientrano nei nostri obblighi quali fornitori e per esse nessun compenso, esplicito o implicito, viene richiesto e/o viene dato. Anche per questo non assumiamo alcuna responsabilità per l'uso di tali informazioni e per i risultati che possono essere ottenuti. Nessuna informazione, raccomandazione o suggerimento può essere intesa ad un impiego in un processo che violi qualsiasi brevetto, copyright o diritto di terzi.

DARACEM sono marchi registrati della GCP Applied Technologies Inc in USA o in altri stati. Questa lista di marchi registrati è stata composta usando le informazioni disponibili alla data di pubblicazione e potrebbero non riflettere accuratamente la proprietà o lo status di essi.

© Copyright 2017 GCP Applied Technologies Inc. Tutti i diritti riservati.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Italiana S.p.A. - Via Trento, 7 - 20017 Passirana di Rho, Milano, Italy

Questo documento è aggiornato solo a partire dalla data dell'ultimo indicato di seguito ed è valido solo per l'uso in Italia. È importante consultare sempre le informazioni attualmente disponibili sull'URL di seguito per avere le informazioni sul prodotto più recenti al momento dell'uso. Documenti aggiuntivi come i manuali di utilizzo, bollettini tecnici, disegni dettagliati e raccomandazioni dettagliate e altri documenti rilevanti sono disponibili anche su www.gcpat.fr. Le informazioni trovate su altri siti web non dovrebbero essere utilizzati, in quanto potrebbero non essere aggiornati o applicabili alle condizioni del tuo paese e non ci assumiamo alcuna responsabilità quanto al loro contenuto. In caso di conflitti o se hai bisogno di ulteriori informazioni, contatta il servizio clienti di GCP.

Last Updated: 2023-06-15

gcpat.it/solutions/products/daracem-100