

DARAVAIR[®] AT30

Air-entraining admixture ASTM C260

Product Description

DARAVAIR[®]AT30 is a liquid air-entraining admixture that provides freeze-thaw resistance, enhances the finishability characteristics of concrete and allows concrete producers to accurately control yield. Daravair AT30 is comprised of a blend of high-grade saponified rosin and organic acid salts and is manufactured under stringent controls, assuring quality and consistent performance. One gallon weighs approximately 8.5 lbs (1.02 kg/L).

Uses

Daravair AT30 is recommended for use in all ready-mix, precast, prestress and other concrete product plants where the intentional entrainment of a specified level of air is required. ACI 201 Guide to Durable Concrete recommends all concrete which is exposed to any level of freeze-thaw exposure or is subjected to the application of de-icing salts during the winter months should be air entrained.

Daravair AT30 has been found to be particularly effective in both high cement factor and low slump concrete mixes, which require a very efficient air-entraining admixture. Daravair AT30 is also utilized when a very stable air void system over time is required.

Performance

Air is incorporated into concrete via mixing mechanics and stabilized into millions of discrete semi-microscopic bubbles in the presence of air-entraining admixtures such as Daravair AT30. These air bubbles act much like flexible ball bearings, thereby increasing the plasticity and workability of the concrete. This allows for reductions in mixing water with no loss of slump. Surface bleeding, plastic shrinkage and aggregate segregation are also minimized.

Through the purposeful entrainment of air, Daravair AT30 markedly increases the durability of concrete to severe exposures, particularly freeze-thaw cycling. It has also demonstrated a remarkable ability to impart resistance to the action of frost and de-icing salts as well as sulfate, sea and alkaline waters.

Product Advantages

- Air stability makes it particularly useful for longer haul times
- Functions well across a wide range of concrete materials

Addition Rates

Daravair AT30 addition rates will vary according to the specified level of air required. Addition rates are also influenced by several variables including: specific mix design parameters, material properties of the cement, fly ash, coarse and fine aggregates and the effects of other chemical admixtures. Other factors such as ambient and concrete temperature, mixing time and time of addition can also affect the required dosage rates. It is recommended that pre-job testing be conducted in order to assure the correct dosage rate of Daravair AT30 is used. Typical Daravair AT30 addition rates range from ¼ to 3 fl oz/100 lbs of cement (15 to 200 mL/100 kg).

Compatibility with Other Admixtures and Batch Sequencing

Daravair AT30 is compatible with most GCP admixtures as long as they are added separately to the concrete mix. In general, it is recommended that Daravair AT30 be added to the concrete mix near the beginning of the batch sequence for optimum performance, preferably by “dribbling” on the sand. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations. Daravair AT30 should not be added directly to heated water.

Pretesting of the concrete mix should be performed before use, as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. Please consult your GCP Applied Technologies representative for guidance.

Packaging & Handling

Daravair AT30 is available in bulk, delivered by metered tank truck, totes and drums.

Daravair AT30 should be protected from temperatures below 32 °F (0 °C), but if freezing does occur, thorough mechanical agitation after thawing will restore it to full strength.

Adhere to SDS (Safety Data Sheet) guidelines when handling product.

Dispensing Equipment

A complete line of accurate dispensing equipment is readily available to dispense Daravair AT30. The dispensers can be installed to discharge the product into the water line, on the sand, or directly in the mixer.

Specifications

The concrete shall be intentionally air entrained, containing a specified level of entrained air. The plastic air content shall be determined by ASTM C231 pressure method, ASTM C173 volumetric method or ASTM C138 gravimetric method. The air entrainment admixture shall be Daravair AT30, as manufactured by GCP Applied Technologies, and will comply with ASTM C260 specification for air-entraining admixtures. The dosage rate of Daravair AT30 will be determined on an individual basis to satisfy the specified requirement for the particular job.

gcpat.it | Servizio clienti in Italia:: +39 02 93537291

Confidiamo che le informazioni date con la presente siano utili. Sono basate su dati e conoscenze che riteniamo vere ed accurate e sono messe a disposizione dell'utente perché li consideri, facendo le opportune verifiche. Tali informazioni non rientrano nei nostri obblighi quali fornitori e per esse nessun compenso, esplicito o implicito, viene richiesto e/o viene dato. Anche per questo non assumiamo alcuna responsabilità per l'uso di tali informazioni e per i risultati che possono essere ottenuti. Nessuna informazione, raccomandazione o suggerimento può essere intesa ad un impiego in un processo che violi qualsiasi brevetto, copyright o diritto di terzi.

DARAVAIR sono marchi registrati della GCP Applied Technologies Inc in USA o in altri stati. Questa lista di marchi registrati è stata composta usando le informazioni disponibili alla data di pubblicazione e potrebbero non riflettere accuratamente la proprietà o lo status di essi.

© Copyright 2017 GCP Applied Technologies Inc. Tutti i diritti riservati.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Italiana S.p.A. - Via Trento, 7 - 20017 Passirana di Rho, Milano, Italy

Questo documento è aggiornato solo a partire dalla data dell'ultimo indicato di seguito ed è valido solo per l'uso in Italia. È importante consultare sempre le informazioni attualmente disponibili sull'URL di seguito per avere le informazioni sul prodotto più recenti al momento dell'uso. Documenti aggiuntivi come i manuali di utilizzo, bollettini tecnici, disegni dettagliati e raccomandazioni dettagliate e altri documenti rilevanti sono disponibili anche su www.gcpat.fr. Le informazioni trovate su altri siti web non dovrebbero essere utilizzati, in quanto potrebbero non essere aggiornati o applicabili alle condizioni del tuo paese e non ci assumiamo alcuna responsabilità quanto al loro contenuto. In caso di conflitti o se hai bisogno di ulteriori informazioni, contatta il servizio clienti di GCP.

Last Updated: 2022-11-24

gcpat.it/solutions/products/daravair-at30