

ESE[®] Non-Chloride Early Strength Enhancing Additives

A Family of Non-Chloride Early Strength Enhancing Additives

Product Description

The ESE[®] series of additives, which involve a newly developed modified alkanolamine, are available for use to enhance the early strength of cement. Unlike other early strength enhancers, ESE cement additives provide their performance benefit without the use of chloride or thiocyanate ions.

ESE products are available in a variety of formulations that are optimized to maximize their performance in different cement types and compositions. All products are also formulated to provide the benefits of traditional grinding aids such as increased grinding efficiency and reduced pack set of finished cement.

Covered by U.S. Patent 6,290,772 and 6,048,393



Physical Properties

Product specifications for the most widely used ESE formulations are as follows:

PRODUCT	S.G.	PH
ESE A951	1.10	9.0-11.0
ESE N948	1.11	9.0-11.0
ESE A937	1.10	9.0-11.0
ESE N938	1.11	9.0-11.0

Specifications for other ESE products are available through GCP Field Engineers.

Benefits

The use of ESE cement additives has been shown to increase the early strength (1, 2 and/or 7 Days) of cement without the addition of chlorides, thereby allowing its use in cements already rich in chloride. ESE additives have performed in all types of cement, including Ordinary Portland and cements blended with slag, fly ash and/or limestone. Early strength (2 Days) increases of up to 22% (versus a blank) have been demonstrated in trials. The resultant high early strength can be used to meet specific market needs or, if desired, the cement producer can trade off the strength increase for reduced cement fineness and **lower unit production costs**. This in turn will result in production increases that can greatly benefit plants that are operating at or near their grinding capacity. Alternatively, the producer can choose to **increase the amount of filler** in the cement, while retaining the previous level of early strength.

The choice of any of these three options will result in incremental savings and/or revenue gains.

Application of ESE Cement Additives

Laboratory mill evaluations of clinker and other additions are recommended prior to field use in order to determine initial blend proportions, evaluate performance parameters and to enable GCP to formulate the most effective ESE product for the specific field use conditions. To arrange for a laboratory evaluation, contact your local GCP Field Engineer.

How to Use

ESE products are sprayed into the mill's first compartment or added onto the clinker or feed conveyor belt. All additives should be accurately proportioned through a calibrated dosing system suitable for the cement mill and for the required output. GCP can provide advice on all types of dosing equipment, including manual, semiautomatic, automatic and computerized systems.

Recommended Addition Rate

According to GCP experience, the dosage of ESE ranges from 250–700 g/t of cement. The optimum addition rate of ESE cement additives should be determined through cement mill tests in consultation with GCP personnel.

Storage

ESE products should be protected from freezing. Once frozen, the product should be thawed out slowly and remixed thoroughly prior to use.

Shelf life is a minimum of 12 months if kept in manufacturer's containers.

Compatibility

The performance of concrete admixtures and the physical properties of concrete are not adversely affected by the use of ESE additives in cement production. ESE additives, and cement treated with ESE additives, are compatible with all commercial concrete admixtures, including air entrainers, water reducers, retarders and superplasticizers.

Case Study — Performance of ESE vs Traditional Chloride Containing Early Strength Enhancers

CEMENT TYPE	I 52.5R	I 52.5R	% CHANGE
Clinker %	95.0	95.0	
Gypsum %	5.0	5.0	
Chloride-based Quality Improver (kg/t)	1.300		
ESE 242 (kg/t)		0.37	
Blaine Fineness (cm ² /gram)	4331	4290	-0.95
Mill Output (t/h)	50	51.7	3.4%
Specific Consumption (kWh/t)	62	60.1	-3.06
W/C Ratio	0.50	0.50	

COMPRESSIVE STRENGTH (MPA): EN 196/1 MORTAR	CHLORIDE QUALITY IMPROVER	ESE 242	% CHANGE
1 Day	27.8	28.0	0.72
2 Days	41.4	44.1	6.52
28 Days	68.1	73.5	7.93

Quality Control

ESE products are carefully controlled and accurately blended for constant quality and optimum performance.

ESE products are ASTM C 465 approved for use in the USA.

Packaging

ESE Early Strength Enhancing Additive is supplied in 210 L (55 gal) drums and ESE products may also be supplied in bulk in certain locations. It contains no flammable material.

gcpat.it | Servizio clienti in Italia:: +39 02 93537291

Confidiamo che le informazioni date con la presente siano utili. Sono basate su dati e conoscenze che riteniamo vere ed accurate e sono messe a disposizione dell'utente perché li consideri, facendo le opportune verifiche. Tali informazioni non rientrano nei nostri obblighi quali fornitori e per esse nessun compenso, esplicito o implicito, viene richiesto e/o viene dato. Anche per questo non assumiamo alcuna responsabilità per l'uso di tali informazioni e per i risultati che possono essere ottenuti. Nessuna informazione, raccomandazione o suggerimento può essere intesa ad un impiego in un processo che violi qualsiasi brevetto, copyright o diritto di terzi.

ESE sono marchi registrati della GCP Applied Technologies Inc in USA o in altri stati. Questa lista di marchi registrati è stata composta usando le informazioni disponibili alla data di pubblicazione e potrebbero non riflettere accuratamente la proprietà o lo status di essi.

© Copyright 2017 GCP Applied Technologies Inc. Tutti i diritti riservati.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Italiana S.p.A. - Via Trento, 7 - 20017 Passirana di Rho, Milano, Italy

Questo documento è aggiornato solo a partire dalla data dell'ultimo indicato di seguito ed è valido solo per l'uso in Italia. È importante consultare sempre le informazioni attualmente disponibili sull'URL di seguito per avere le informazioni sul prodotto più recenti al momento dell'uso. Documenti aggiuntivi come i manuali di utilizzo, bollettini tecnici, disegni dettagliati e raccomandazioni dettagliate e altri documenti rilevanti sono disponibili anche su www.gcpat.fr. Le informazioni trovate su altri siti web non dovrebbero essere utilizzati, in quanto potrebbero non essere aggiornati o applicabili alle condizioni del tuo paese e non ci assumiamo alcuna responsabilità quanto al loro contenuto. In caso di conflitti o se hai bisogno di ulteriori informazioni, contatta il servizio clienti di GCP.

Last Updated: 2022-11-24

gcpat.it/solutions/products/gcp-performance-enhancers/ese-non-chloride-early-strength-enhancing-additives