

# WRDA<sup>®</sup> 60

Water-reducing admixture ASTM C494 Type A and D

---

## Product Description

WRDA<sup>®</sup>60 is a polymer based aqueous solution of complex organic compounds. WRDA 60 is a ready-to-use low viscosity liquid which is produced under rigorous quality control to provide uniform, predictable performance. WRDA 60 does not contain added calcium chloride and weighs approximately 9.59 lbs/gal (1.15 kg/L).

## Uses

WRDA<sup>®</sup>60 produces concrete with lower water content (typically 8%–10% water reduction), improved workability and higher strengths. It is used in ready-mix block and concrete product plants.

## Advantages

WRDA 60 offers significant advantages over single component water reducers. Water reduction and setting times are more consistent due to the polymer contents. WRDA 60 performs especially well in warm and hot weather climates to maintain slump and workability in high ambient temperatures.

The use of WRDA 60 produces a plastic concrete that is more workable, easier to place and more finishable than plain concrete. In the hardened state WRDA 60 concrete has higher compressive strengths at all ages than untreated concrete.

## Finishability

WRDA 60 produces workable concrete with improved finishability and workability. The influence of WRDA 60 on lean mixes will be particularly noticeable. Floating and troweling, by machine or by hand, imparts a smooth, close surface tolerance.

## Product Advantages

- Consistent water reduction and set times
- Improves performance concrete containing supplementary cementitious materials
- Produces concrete that is more workable, easy to place and finish
- High compressive and flexural strengths

## Addition Rates

WRDA 60 provides water reduction and minimal retardation, through mild and extended retardation, as job site conditions require. As addition rates are increased, set times will be extended proportionately.

The addition rate of WRDA 60 is 3 to 10 fl oz/ 100 lbs (195 to 625 mL/100 kg) cementitious material. Pretesting is recommended to determine the optimum addition rate. Optimum addition rate is determined by other concrete mixture components, job site conditions and desired performance characteristics.

## Compatibility with Other Admixtures and Batch Sequencing

WRDA 60 is compatible with most GCP admixtures as long as they are added separately to the concrete mix, usually through the water holding tank discharge line. In general, it is recommended that WRDA 60 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

Pretesting of the concrete mix should be performed before use, as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as DARAVAIR® or DAREX® product lines) is recommended to provide suitable air void parameters for freeze-thaw resistance. Due to a synergistic effect of WRDA 60, the quantity of air-entraining agent added to WRDA 60 may be reduced by 25 to 50%. Please consult your GCP Applied Technologies representative for guidance.

## Packaging & Handling

WRDA 60 is available in bulk, delivered by metered tank trucks, totes and drums.

WRDA 60 will freeze at about 28°F (-2°C) but will return to full strength after thawing and thorough mechanical agitation.

## Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available. WRDA 60 may be introduced into the mix on the sand or in the mix water.

## Specifications

Concrete shall be designed in accordance with *Standard Recommended Practice for Selecting Proportions for Concrete*, ACI 211.

The water-reducing admixture shall be WRDA 60 as manufactured by GCP Applied Technologies, or approved equal. The admixture shall not contain calcium chloride. It shall meet the requirements of *Specification for Chemical Admixtures for Concrete* ASTM Designation C494 as a Type D admixture when used at an addition rate of 3 to 10 fl oz/100 lbs (190 to 625 mL/100 kg) of cementitious material. WRDA 60 is NSF Std. 61 certified when used at a maximum addition rate of 6 fl oz/100 lbs (390 mL/100 kg) of cementitious material.

The admixture shall be delivered as a ready-to-use liquid product and shall require no mixing at the batching plant or job site.

**gcpat.it | Servizio clienti in Italia:: +39 02 93537291**

Confidiamo che le informazioni date con la presente siano utili. Sono basate su dati e conoscenze che riteniamo vere ed accurate e sono messe a disposizione dell'utente perché li consideri, facendo le opportune verifiche. Tali informazioni non rientrano nei nostri obblighi quali fornitori e per esse nessun compenso, esplicito o implicito, viene richiesto e/o viene dato. Anche per questo non assumiamo alcuna responsabilità per l'uso di tali informazioni e per i risultati che possono essere ottenuti. Nessuna informazione, raccomandazione o suggerimento può essere intesa ad un impiego in un processo che violi qualsiasi brevetto, copyright o diritto di terzi.

WRDA sono marchi registrati della GCP Applied Technologies Inc in USA o in altri stati. Questa lista di marchi registrati è stata composta usando le informazioni disponibili alla data di pubblicazione e potrebbe non riflettere accuratamente la proprietà o lo status di essi.

© Copyright 2017 GCP Applied Technologies Inc. Tutti i diritti riservati.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Italiana S.p.A. - Via Trento, 7 - 20017 Passirana di Rho, Milano, Italy

Questo documento è aggiornato solo a partire dalla data dell'ultimo indicato di seguito ed è valido solo per l'uso in Italia. È importante consultare sempre le informazioni attualmente disponibili sull'URL di seguito per avere le informazioni sul prodotto più recenti al momento dell'uso. Documenti aggiuntivi come i manuali di utilizzo, bollettini tecnici, disegni dettagliati e raccomandazioni dettagliate e altri documenti rilevanti sono disponibili anche su [www.gcpat.fr](http://www.gcpat.fr). Le informazioni trovate su altri siti web non dovrebbero essere utilizzati, in quanto potrebbero non essere aggiornati o applicabili alle condizioni del tuo paese e non ci assumiamo alcuna responsabilità quanto al loro contenuto. In caso di conflitti o se hai bisogno di ulteriori informazioni, contatta il servizio clienti di GCP.

Last Updated: 2023-06-15

[gcpat.it/solutions/products/wrda-60](http://gcpat.it/solutions/products/wrda-60)